$\begin{array}{l} \textbf{3M} \\ \textbf{Scotch-Weld}^{\text{TM}} \\ \textbf{General Purpose Instant Adhesives} \\ \text{EC5} \cdot \text{EC40} \cdot \text{EC100} \cdot \text{EC2500} \cdot \text{ECI Gel} \end{array}$

Technical Data	April 2016
Product Description	3M [™] Scotch-Weld [™] General Purpose Instant Adhesives are single component, high strength ethyl cyanoacrylate adhesives designed to bond to a variety of substances including most plastics, rubbers, metals, and other common substrates. They are available in a wide variety of viscosities.
Specific Features	• 3M [™] Scotch-Weld [™] General Purpose Instant Adhesive EC5 is a very low viscosity, cyanoacrylate that is fast bonding. It is recommended for use on assemblies with very close-fitting parts and smooth, even surfaces. It can be used to wick into bonding gaps of assembled parts.
	• 3M TM Scotch-Weld TM General Purpose Instant Adhesive EC40 is a low viscosity cyanoacrylate that is fast curing. It is recommended for use on assemblies with close-fitting parts and smooth, even surfaces.
	• 3M [™] Scotch-Weld [™] General Purpose Instant Adhesive EC100 is a low viscosity cyanoacrylate that is fast curing and useful for general purpose bonding.
	• 3M TM Scotch-Weld TM General Purpose Instant Adhesive EC600 is a medium viscosity cyanoacrylate that resists migration from the bond area. It can be used for wire tacking on printed circuit boards.
	• 3M TM Scotch-Weld TM General Purpose Instant Adhesive EC2500 is a hig viscosity liquid cyanoacrylate with an even slower cure rate. It is also used o assemblies where parts are not close-fitting, surfaces are rough or porous, or when time is required to align parts before cure.
	• 3M TM Scotch-Weld TM General Purpose Instant Adhesive ECI Gel is an industria strength thixotropic gel for maximum gap filling. It is suitable for bonding poorl mating components and for porous substrates such as ceramic and can be used o vertical surfaces as it will not drip or slump.

3M[™] Scotch-Weld[™] General Purpose Instant Adhesives

EC5 • EC40 • EC100 • EC2500 • ECI Gel

Typical Uncured	Note: The following technical information and data should be considered representative or
Physical Properties	typical only and should not be used for specification purposes.

	3M™ Scotch-Weld™ General Purpose Instant Adhesive				
	EC5*	EC40	EC100	EC2500	ECI Gel
Color	Clear	Clear	Clear	Clear	Clear
Base	Ethyl	Ethyl	Ethyl	Ethyl	Ethyl
Appearance	Liquid	Liquid	Liquid	Liquid	Liquid
Specific Gravity (g/ml)	1.05	1.06	1.06	1.08	1.10
Viscosity (cps)	<= 5 ¹	20 – 45 ¹	70-100 ¹	2,000 – 3,000 ²	100,000 – 150,000 ³
Time to Handling Strength (sec) *	<10	<15	<20	<40	<25
Time to full cure (hr)	24	24	24	24	24

¹ Cone-Plate viscosity, CP75 at 3000/s shear rate; ² Cone-Plate viscosity, CP50 at 100/s shear rate; ³ Brookfield viscosity, Spindle TC @ 2.5 rpm;; * On EPDM. Time to handling is substrate dependent.

Typical Cured Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

	3M™ Scotch-Weld™ General Purpose Instant Adhesive				
	EC5	EC40	EC100	EC2500	ECI Gel
Temperature Range (°F)	-60 to 180	-60 to 180	-60 to 180	-60 to 180	-60 to 180
Gap Fill (in)	0.002	0.004	0.006	0.008	0.010
	Overlap Shear Strength (psi) ¹				
Steel ²	2000	2000	2100	2100	2100
Stainless Steel ²	2150	2400	2000	2400	3100
Aluminum ²	1600	1700	1650	2100	3150
ABS	950 ³	1000 ³	990 ³	850 ³	1300 ³
Polycarbonate	900 ³	800 ³	800 ³	800 ³	1000 ³
PVC	1200 ³	1200 ³	1800 ³	1200 ³	1450 ³
Nylon	350	400	750	500	350
Polypropylene ⁴	750 ³	800 ³	950 ³	1050 ³	830 ³
Silicone Elastomers ⁵	100 ³	100^{3}	100^{3}	110 ³	100 ³

¹ ASTM D-1002 ² Grit blasted ³ Substrate failure ⁴ Primed with AC77 ⁵ Primed with AC79

3M[™] Scotch-Weld[™] General Purpose Instant Adhesives EC5 • EC40 • EC100 • EC2500 • ECI Gel

	Percent of Initial Strength				
Temp (F)	EC5	EC40	EC100	EC2500	EC Gel
72	100	100	100	100	100
167	82	96	82	94	90
212	73	71	65	78	47
257	29	20	28	24	15

Handling Information

Surface Preparation

For optimum strength structural bonds, paint, oxide films, oils, dust, mold release agents, and all other surface contaminants must be completely removed. However, the amount of surface preparation depends on the required bond strength and the environmental aging resistance desired by the user. Typical quick surface preparation would include wiping with a clean solvent (such as isopropyl alcohol*), abrading the surface with a clean fine abrasive, and then wiping again with a clean solvent to remove loose particles.

Directions for Use

- 1. Ensure that parts are clean, dry, and free from oil and grease.
- 2. An instant adhesive activator may be required if there are bonding gaps or porous substrate surfaces, if substrates are low surface energy plastics (e.g., polyethylene, polypropylene) or if substrates have acidic surfaces (e.g., paper, leather).
- 3. Bond speed is typically very fast so ensure that parts are properly aligned before dispensing.
- 4. Product is normally hand applied from the bottle. Apply sparingly to one surface and press parts firmly together until handling strength is achieved. As a general rule, as little cyanoacrylate as possible should be used. Over application will result in slower cure speed and lower bond strength.

Cured Bond Characteristics

- 1. Full bond strength will typically be achieved within a 24 hour cure time.
- 2. Low humidity or low temperature conditions will slow down the cure rate.
- 3. After curing, 3M[™] Scotch-Weld[™] General Purpose Instant Adhesive bonds are suitable for use up to about 180°F (82°C).
- 4. Cyanoacrylate bond resistance to most oils and solvents is excellent. Long term humidity, moisture, or water immersion may affect the strength of a cured cyanoacrylate bond depending on the substrates and the bond gap. Testing is recommended to evaluate the effect.
- *Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

$\begin{array}{l} \textbf{3M}^{\text{\tiny TM}} \textbf{ Scotch-Weld}^{\text{\tiny TM}} \\ \textbf{General Purpose Instant Adhesives} \\ \text{EC5} \bullet \text{EC40} \bullet \text{EC100} \bullet \text{EC2500} \bullet \text{ECI Gel} \end{array}$

Storage	For short term storage (<30 days), keep adhesive in a cool (60° F to 80° F [16° C to 27°C]), dry place out of direct sunlight. Keep containers tightly covered and free of moisture. Refrigeration (40° F [4° C]) gives optimum long term storage stability.
Shelf Life	3M TM Scotch-Weld TM General Purpose Instant Adhesives can be expected to have a shelf life of one year from the date of shipment from 3M when stored under refrigerated conditions.
Precautionary Information	Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.
Technical Information	The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.
Product Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001:2000

This product was manufactured under a quality system registered to ISO 9001:2000 standards.

ЗМ

Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-362-3550 • 877-369-2923 (Fax) www.3M.com/structuraladhesives